



PRELIMINARY DATA SHEET

Witcom PA6-2008/334, based on Polyamide 6 (PA6)

reinforced, thermally conductive, electrically conductive

| Properties | Test method | Unit | PA6-2008/334 |
|------------|-------------|------|--------------|
|------------|-------------|------|--------------|

Physical properties

| | | | |
|--|----------|-------------------|-----------|
| Specific gravity | ISO 1183 | g/cm ³ | 1,56 |
| Water absorption at saturation, 23 °C | ISO 62 | % | 3,5 |
| Humidity absorption, 23 °C/50 % RH | ISO 62 | % | 1,2 |
| Mould shrinkage (flow direction, 3 mm) | ISO 2577 | % | 0,2 - 0,5 |

Mechanical properties

| | | | |
|---------------------------------|-------------|-------------------|------|
| Tensile strength (max.) | ISO 527 | MPa | 50 |
| Elongation at break | ISO 527 | % | 0,5 |
| Flexural strength | ISO 178 | MPa | 90 |
| Flexural modulus | ISO 178 | GPa | 20,0 |
| IZOD impact strength, notched | ISO 180/1eA | kJ/m ² | 2,5 |
| IZOD impact strength, unnotched | ISO 180/1eU | kJ/m ² | 10 |

Thermal properties

| | | | |
|--|------------|----------------------|----|
| Heat distortion temperature (1,81 MPa) | ISO 75 | °C | - |
| Relative temperature index, 3 mm with impact | UL 746B | °C | 90 |
| Coefficient of linear thermal expansion | ISO 11359 | K-1·10 ⁻⁵ | - |
| Thermal conductivity* | ASTM E1530 | W/mK | 6 |

Flammability

| | | | |
|-------------------|----------|---|-------------|
| Burning behaviour | ISO 1210 | - | HB @ 3,0 mm |
| UL recognition | UL94 | - | - |

Electrical properties

| | | | |
|----------------------------|-------------|------|-----------------------------------|
| Surface resistivity | ASTM D257 | Ω/sq | 10 ¹ - 10 ³ |
| Volume resistivity | ASTM D257 | Ω·cm | 10 ¹ - 10 ³ |
| Comparative tracking index | IEC 60112 | V | - |
| Glow wire rating, 1,6 mm | IEC 695-2-1 | °C | - |

* through plane

Revision date: 21-11-2008

This information is based on our experience to date and we believe it to be reliable. It is intended as a guide for use at your discretion and risk. We cannot guarantee favourable results and assume no liability in connection with the use of the product described. None of this information is to be taken as a license to operate under, or a recommendation to infringe, any patents.